

Raman signal amplifying membrane filters for nanoplastic research

Joona Huopala^{1*}, Arto Hiltunen², Pia Damlin¹, Sirkku Häkkinen² & Jari Hänninen²

¹Materials Chemistry Research Group, Department of Chemistry, University of Turku

²Biodiversity Unit of the University of Turku

Background








Due to the rapidly increased production of plastic and inadequate waste treatment, more and more plastic ends up in our waters every day. Plastic can degrade to smaller micro- (1 μm – 5 mm) and nanoplastics (< 1 μm) e.g. under mechanical abrasion and UV-light. In addition to the damage of marine life, the small plastic waste has raised concerns regarding to human health. Nanoplastics can enter cells or even penetrate the blood-brain barrier. [1,2]

Aim of this work

The main goal of this project is to develop a method, that can be used to image and detect nanoplastics from seawater. In this work we focused on improving the detection of nanoplastics with Raman-microscope by using surface-enhance Raman spectroscopy/scattering (SERS). Also, the sample processing was simplified by using membrane filter as a SERS substrate.

Materials and Methods

Thin layers of gold and platinum were deposited on Al_2O_3 membrane filters (pore size: 200 nm) via sputtering. Scanning electron microscope (SEM) was used to characterize the morphology of the membranes. Polystyrene (PS) spheres (diameter: 500 nm) in aqueous solution was deposited on to these membranes by vacuum filtration. Raman-microscope was used to measure Raman-spectra of 3 individual PS spheres on each membrane.



Results

- PS nanoplastics are more visible against the colored Au and Pt backgrounds in microscopic images.
- Better Raman signal is obtained from PS nanoplastics when the membrane is coated with thin Au or Pt layer.
- Since nanoplastics can be detected directly from the membrane filter, less processing is needed.

References

1. Lim, X., Nature 2021, 593, 22-25.
2. Mandemaker, L. D. B. ja Meirer, F., Angew. Chem. Int. Ed. 2023, 62.

Acknowledgement

The study has utilized research infrastructure facilities provided by FINMARI (the Finnish Marine Research Infrastructure consortium).



UNIVERSITY
OF TURKU

